

(12) UK Patent Application (19) GB (11) 2 114 586 A

(21) Application No 8302689

(22) Date of filing
1 Feb 1983

(30) Priority data

(31) 8201868

(32) 5 Feb 1982

(33) France (FR)

(43) Application published

24 Aug 1983

(51) INT CL³ C08J 5/14

C08K 7/10

C08L 61/10

F16D 69/02

(52) Domestic classification

C3R 1C C15 C1 C22

C29 C33A C5B1 C6A1

C6AX C6B C6X C8P

L2CX L3A L3B L4D V

C3V DA

C3W 203 213 326 327

U1S 1363 2013 2014

C3R C3V

(56) Documents cited

None

(58) Field of search

C3R

C3V

C3K

(71) Applicant

VALEO

(France)

64 Avenue de la Grande

Arme

75017 Paris

France

(72) Inventors

Pierre Leroy

Michel Pilache

(74) Agent and/or Address for

Service

Page White and Farrer

5 Plough Place

New Fetter Lane

London EC4A 1HY

(54) Friction lining suitable for use
in brakes and clutches

(57) A friction lining suitable for
brakes, clutches etc. comprises min-
eral fibres which contain alumina,
 Al_2O_3 , silica, SiO_2 , and lime, CaO .
The mineral fibres have a percent-
age by weight of alumina, Al_2O_3 ,
of between 18% and 25%, a per-
centage by weight of silica, SiO_2 , of
between 38% and 45% and a per-
centage by weight of lime, CaO , of
between 23% and 33% and prefer-
ably of the order of 27%. More-
over, the mineral fibres contain iron
oxide, Fe_2O_3 , in a proportion by
weight of between 0.5% and 1%,
alkali metal oxides, Na_2O and K_2O ,
in a proportion by weight of be-
tween 4% and 10% and magnesia,
 MgO , in a proportion by weight of
between 0.5% and 3%. Fibres hav-
ing substantially the same compo-

sition, or a mixture of fibres of
different compositions, e.g. a mix-
ture of slag fibres and basalt fibres,
may be used.

GB 2 114 586 A

SPECIFICATION

Friction lining suitable for use in brakes, clutches and other applications

- 5 The present invention relates to a friction lining, in particular for use in brakes, clutches and other applications, having mineral fibres which contain alumina, Al_2O_3 , silica, SiO_2 , and lime, CaO. 5

In friction linings of this type, it has already been proposed to use slag fibres and also basalt fibres as mineral fibres.

- 10 In general, slag fibres have a percentage by weight of alumina, Al_2O_3 , of between 10% and 15%, a percentage by weight of silica, SiO_2 , of between 38% and 45% and a percentage by weight of lime CaO, of between 35% and 45%, while basalt fibres have a percentage by weight of alumina, Al_2O_3 , of between 10% and 20%, a percentage by weight of silica, SiO_2 , of between 38% and 46% and a percentage by weight of lime, CaO, of between 10% and 18%. 10

- 15 The Applicants have found that friction linings containing slag fibres are relatively brittle in contrast to friction linings containing basalt fibres, which frequently have an excessive aggressiveness towards the counter-material, such as the disc, ring, drum or plate, with which the friction lining interacts by rubbing. 15

- 20 Experiments carried out by the Applicants have shown that the proportion of lime, CaO, in the mineral fibres is of prime importance in determining the brittleness and the aggressiveness of the friction lining. 20

- The relatively high percentage of lime, CaO, of between 35% and 45% in slag fibres would explain the brittleness of linings containing slag fibres, while the relatively low percentage of lime, CaO, of between 10% and 18% in basalt fibres would explain the aggressiveness towards the counter-material of friction linings containing basalt fibres. 25

- 25 Experiments have shown that mineral fibres having a smaller proportion of lime, CaO, than in the case of slag fibres, but a higher proportion thereof than in the case of basalt fibres have the effect of substantially reducing the brittleness and also the aggressiveness of the friction lining.

- 30 The present invention relates to a friction lining, in particular for brakes, clutches and other applications, having mineral fibres which contain alumina, Al_2O_3 , silica, SiO_2 , and lime, CaO, and which possess excellent rubbing characteristics and good properties as regards both the robustness and the absence of aggressiveness towards the counter-material. 30

- 35 According to the invention, a friction lining, in particular for brakes, clutches and other applications, having mineral fibres which contain alumina, Al_2O_3 , silica, SiO_2 , and lime, CaO, is characterised in that the said fibres have overall a percentage by weight of lime, CaO, of between 23% and 33% and preferably of the order of 27%. 35

- By virtue of this arrangement, the friction lining containing such mineral fibres with this percentage by weight of lime, CaO, is particularly robust and does not cause any deterioration in the counter-material.

- 40 In one embodiment, each fibre of the lining has substantially the same composition, while, as a variant, the lining contains a mixture of fibres of different compositions. 40

- According to other characteristics of the invention, the mineral fibres of the friction lining have a percentage by weight of alumina, Al_2O_3 , of between 18% and 25% and a percentage by weight of silica, SiO_2 , of between 38% and 45%.

- 45 Moreover, the mineral fibres preferably contain iron oxide, Fe_2O_3 , in a proportion by weight of between 0.5% and 1%, alkali metal oxides, Na_2O and K_2O , in a proportion by weight of between 4% and 10% and magnesium, MgO, in a proportion by weight of between 0.5% and 3%. 45

- Excellent results have been obtained with these various constituents in the proportions indicated. In particular, the friction lining has good heat resistance characteristics, due to the relatively high proportion of alumina, Al_2O_3 , of between 18% and 25% and to the proportion of magnesium, MgO, of between 0.5% and 3%. 50

- According to another characteristic, the mineral fibres advantageously have a diameter of between 3 and 20 microns, and preferably of the order of 10 microns. This relatively large diameter is totally consistent with the conditions desirable for health and safety at work. 55

Examples are given below without implying a limitation.

EXAMPLE I

- A friction lining for a disc brake sector has mineral fibres. 60
These mineral fibres contain alumina, Al_2O_3 , silica, SiO_2 , lime, CaO, iron oxide, Fe_2O_3 , alkali metal oxides, Na_2O and K_2O , and magnesium, MgO, in the following proportions by weight: 60

	Alumina, Al_2O_3 :	between 18% and 25%	
	Silica, SiO_2 :	between 38% and 45%	
	Lime, CaO :	between 23% and 33%	
5	Iron oxide, Fe_2O_3 :	between 0.5% and 1%	5
	Alkali metal oxides, Na_2O and K_2O :	between 4% and 10%	
	Magnesia, MgO :	between 0.5% and 3%	

10 More particularly, in this example, the proportions by weight of the constituents of the mineral fibres are as follows: 10

	Alumina, Al_2O_3	18%	
	Silica, SiO_2	38%	
15	Lime, CaO	33%	15
	Iron oxide, Fe_2O_3	0.5%	
	Alkali metal oxides, Na_2O and K_2O	10%	
	Magnesia, MgO	0.5%	

20 To form these mineral fibres, their constituents are mixed and melted in a crucible; a molten jet leaves the crucible and is treated in spinnerets, or on centrifugation discs, or by means of gas jets, so as to give a fibre diameter of between 3 and 30 microns and preferably of the order of 10 microns. 20

25 To form the friction lining, a wool is used which consists of the mineral fibres just described and also other constituents in the following proportions: 25

30	Constituents	Range of percentages	Preferred percentage	30
	phenol/formaldehyde resin	11% to 21%	16%	
	cardolite	7% to 13%	10%	
	powdered rubber waste	2% to 4%	3%	
35	barium sulphate	10% to 20%	15%	35
	Meudon white	7% to 13%	10%	
	cyanite	3% to 7%	5%	
	brass wool	4% to 8%	6%	
40	wool formed of the mineral fibres	25% to 45%	35%	40

A mixture is formed with these various constituents, pelletised under a pressure of 200 bars and heated in a mould for 15 minutes at a temperature of $140^\circ C$ and under a pressure of 300 bars. The pellet thus obtained is stabilised by superheating in an oven for 5 hours at a temperature of $220^\circ C$. 45

The friction lining thus obtained possesses excellent rubbing characteristics and also good properties, in particular as regards its robustness and its absence of aggressiveness towards the counter-material formed by the disc of a disc brake. 50

EXAMPLE II

This example relates to an organometallic lining for a disc brake.

This lining contains a wool formed of mineral fibres produced as described in Example I, but comprising constituents in the following proportions by weight: 55

	Alumina, Al_2O_3	22%	
	Silica, SiO_2	40%	
	Lime, CaO	29%	
	Iron oxide, Fe_2O_3	1%	
60	Alkali metal oxides, Na_2O and K_2O	5%	60
	Magnesia, MgO	3%	

The lining comprises the following constituents in the following proportions by weight:

	Constituents	Range of percentages	Preferred percentage	
5	phenol/formaldehyde resin	5% to 11%	8%	5
	graphite	2% to 4%	3%	
	carbon black	1% to 3%	2%	
	coke	7% to 13%	10%	
10	Molybdenum sulphide	1% to 3%	2%	10
	copper powder	3% to 7%	5%	
	steel wool	25% to 76%	30%	
	iron powder	0% to 50%	28%	
15	wool formed of mineral fibres	8% to 16%	12%	15

A mixture comprising these constituents is pelletised under a pressure of 200 bars and heated for 15 minutes at a temperature of 140°C and under a pressure of 750 bars. The pellet is stabilised by superheating in an oven for 2 hours at 250°C.

The lining thus obtained possesses excellent rubbing characteristics and also an excellent wear resistance together with an absence of aggressiveness towards the counter-material formed by a brake disc.

25 EXAMPLE III

This example relates to a friction lining for a drum brake.

The lining contains a wool formed of mineral fibres produced as described in Example I, but having the following constituents in the following proportions:

30	Alumina, Al_2O_3	25%	30
	Silica, SiO_2	45%	
	Lime, CaO	23%	
	Iron oxide, Fe_2O_3	0.5%	
35	Alkali metal oxides, Na_2O and K_2O	4%	35
	Magnesia, MgO	2.5%	

The lining comprises the following constituents in the following proportions by weight:

	Constituents	Range of percentages	Preferred percentage	
	phenol/formaldehyde resin	17% to 33%	25%	
45	powdered rubber waste	3% to 7%	5%	45
	cardolite	5% to 11%	8%	
	tin powder	1% to 3%	2%	
	barium sulphate	10% to 20%	15%	
	iron oxide	3% to 7%	5%	
50	wool comprising the mineral fibres	25% to 55%	40%	50

This mixture is pelletised to the required shape. It is heated in a mould at a temperature of 140°C and under a pressure of 75 bars. The pellet is stabilised by superheating in an oven for 8 hours at 200°C.

The lining thus obtained possesses excellent rubbing characteristics and also a good resistance and an absence of aggressiveness towards the counter-material formed by the brake drum.

60 EXAMPLE IV

This example relates to a clutch lining obtained by winding a filament impregnated with an impregnating cement.

The filament consists of a wool comprising mineral fibres having the composition according to Example I, fibrane and cooper.

The filament has the following composition in percentages by weight:

60

65

Constituents	Range of percentages	Preferred percentage
wool formed of mineral fibres	30% to 50%	40%
fibranne	30% to 50%	40%
copper	15% to 25%	20%

A base filament comprises the mineral wool and the fibranne and is obtained by the process which consists in mixing, carding and then twisting together the two fibres. The copper filament can be introduced during twisting or simply combined with the filament comprising the mineral wool and the fibranne at the time of impregnation.

The impregnating cement comprises the following constituents in the following proportions by weight:

Constituents	Range of percentages	Preferred percentage
styrene/butadiene rubber, SBR	10% to 20%	15%
phenol/formaldehyde resin	7% to 13%	10%
carbon black	7% to 13%	10%
graphite	2% to 4%	3%
galena	10% to 20%	15%
Meudon white	7% to 13%	10%
barium sulphate	12% to 22%	17%
kaolin	3% to 13%	10%
zircon	3% to 7%	5%
sulphur	3% to 7%	5%

The impregnating cement consists of a suspension of pulverulent fillers in a solution of styrene/butadiene rubber, SBR, in trichloroethylene.

The filament which has been described above is impregnated continuously in this cement and then dried.

The proportion by weight of the filament and of the cement in the lining is between 40% and 70% for the filament and between 30% and 60% for the cement. Preferably, the proportion by weight is 90 grams of dry cement per 100 grams of filament. The impregnated and dried filament is then wound in the form of a ring, which constitutes the blank of a disc. This is heated in a mould for 20 minutes at a temperature of 160°C and under a pressure of 500 bars. It is stabilised by superheating in an oven for 10 hours at a temperature of 180°C.

The clutch lining thus obtained possesses excellent rubbing characteristics. It has a high robustness and is not aggressive towards the counter-material formed by the clutch plates.

EXAMPLE V

This example relates to a friction lining for a disc brake pad. This lining, which contains a mixture of slag fibres and basalt fibres, the composition of which corresponds overall to a lime content of 28%, combines a sufficient mechanical strength, by virtue of the basalt fibres, with a very low aggressiveness towards the counter-material, by virtue of the presence of slag fibres.

The basalt fibres have the following composition by weight:

Alumina	15%
Silica	42%
Lime	14%
Iron oxide	16%
Magnesia	13%

and the slag fibres have the following composition by weight:

	Alumina	12%	
	Silica	38%	
	Lime	42%	
5	Iron oxide	0.5%	5
	Magnesia	7.5%	

A mixture of basalt fibres and slag fibres is used to form a friction lining of which the constituents are in the following proportions by weight:

10 10

	Constituents	% ranges	Preferred %	
	phenol/formaldehyde resin	11 to 21	16	
15	cardolite	7 to 13	10	15
	powdered rubber waste	2 to 14	3	
	barium sulphate	10 to 20	15	
	Meudon white	7 to 13	10	
	cyanite	3 to 7	5	
20	brass wool	4 to 8	6	20
	basalt wool	12.5 to 22.5	17.5	
	slag wool	12.5 to 22.5	17.5	

25 A mixture is formed with these various constituents, pelletised under a pressure of 200 bars and heated in a mould for 15 minutes at a temperature of 140°C and under a pressure of 300 bars. The pellet thus obtained is stabilised by superheating in an oven for 5 hours at 220°C.

The friction lining thus obtained possesses excellent rubbing characteristics and also good properties, in particular as regards its robustness. The aggressiveness towards the counter-material, although low, is more substantial than in the previous examples, but is still acceptable.

CLAIMS

1. A friction lining, suitable for brakes, clutches and other applications, comprising mineral fibres which contain alumina, Al_2O_3 , silica, SiO_2 , and lime, CaO, wherein the said fibres have an overall percentage by weight of lime, CaO, of between 23% and 33%.

2. A friction lining according to Claim 1, wherein each fibre has substantially the same composition.

3. A friction lining according to Claim 1, wherein the lining contains a mixture of fibres of different compositions.

4. A friction lining according to Claim 3, wherein the fibres of different compositions are, on the one hand, slag fibres, and, on the other hand, basalt fibres.

5. A friction lining according to Claim 4, wherein the slag fibres and the basalt fibres are in substantially identical proportions.

6. A friction lining according to any one of Claims 1 to 5, wherein the said mineral fibres have an overall percentage by weight of alumina, Al_2O_3 , of between 18% and 25%.

7. A friction lining according to any one of Claims 1 to 6, wherein the said mineral fibres have an overall percentage by weight of silica, SiO_2 , of between 38% and 45%.

8. A friction lining according to any one of Claims 1 to 7, wherein the said mineral fibres contain iron oxide, Fe_2O_3 , in an overall proportion by weight of between 0.5 and 1%.

9. A friction lining according to any one of Claims 1 to 8, wherein the said mineral fibres contain alkali metal oxides, Na_2O and K_2O , in an overall proportion by weight of between 4% and 10%.

10. A friction lining according to any one of Claims 1 to 9, wherein the said mineral fibres contain magnesia, MgO, in an overall proportion by weight of between 0.5% and 3%.

11. A friction lining according to any one of Claims 1 to 10, wherein the proportion by weight of the said mineral fibres in the friction lining is between 10% and 55%.

12. A friction lining according to any one of Claims 1 to 11, wherein said lining contains not only the said mineral fibres but also all or some of the following constituents: phenol/formaldehyde resin, cardolite, powdered rubber waste, barium sulphate, coke Meudon white, cyanite, brass wool, graphite, carbon black, molybdenum sulphide, copper powder, steel wool, iron powder, tin powder and iron oxide.

13. A friction lining according to Claim 12, wherein the proportions by weight of the said constituents in the lining are as follows:

	phenol/formaldehyde resin	: between 5% and 33%	
	cardolite	: between 0% and 13%	
	powdered rubber waste	: between 2% and 7%	
5	barium sulphate	: between 7% and 20%	5
	coke	: between 0% and 13%	
	Meudon white	: between 0% and 13%	
	cyanite	: between 0% and 7%	
	brass wool	: between 0% and 8%	
10	graphite	: between 0% and 4%	10
	carbon black	: between 0% and 3%	
	molybdenum sulphide	: between 0% and 3%	
	copper powder	: between 0% and 7%	
	steel wool	: between 0% and 76%	
15	iron powder	: between 0% and 50%	15
	tin powder	: between 0% and 3%	
	iron oxide	: between 0% and 7%	

14. A friction lining according to any one of Claims 1 to 12, wherein the lining contains a mixture of basalt fibres and slag fibres with constituents in the following proportions by weight: 20

	phenol/formaldehyde resin	: between 11% and 21%	
	cardolite	: between 7% and 13%	
	powdered rubber waste	: between 2% and 4%	
25	barium sulphate	: between 10% and 20%	25
	Meudon white	: between 7% and 13%	
	cyanite	: between 3% and 7%	
	brass wool	: between 4% and 8%	
	basalt wool	: between 12.5% and 22.5%	
30	slag wool	: between 12.5% and 5%	30

15. A friction lining according to any one of Claims 1 to 11, wherein the lining comprises a filament impregnated with a cement, the said filament containing the said mineral fibres, fibranne and copper filament, while the cement contains all or some of the following constituents: styrene/butadiene rubber, SBR, phenol/formaldehyde resin, carbon black, graphite, galena, Meudon white, barium sulphate, kaolin, zircon and sulphur. 35

16. A friction lining according to Claim 15, wherein the proportions by weight of the filament and the cement in the lining are as follows:

40	filament	: between 40% and 70%	40
	cement	: between 30% and 60%	

the proportions by weight of the constituents of the filament in the filament are as follows:

45	mineral fibres	: between 30% and 50%	45
	fibranne	: between 30% and 50%	
	copper filament	: between 15% and 25%	

and the proportions by weight of the constituents of the cement in the cement are as follows:

50	styrene/butadiene rubber, SBR	: between 10% and 20%	50
	phenol/formaldehyde resin	: between 7% and 13%	
	carbon black	: between 7% and 13%	
	graphite	: between 2% and 4%	
55	galena	: between 10% and 20%	55
	Meudon white	: between 7% and 13%	
	barium sulphate	: between 12% and 22%	
	kaolin	: between 7% and 13%	
	zircon	: between 3% and 7%	
60	sulphur	: between 3% and 7%	60

17. A friction lining according to any one of Claims 1 to 16, wherein the said mineral fibres have a diameter of between 3 and 20 microns and preferably of the order of 10 microns.

18. A friction lining according to Claim 1, wherein the said fibres have an overall percentage 65 by weight of lime, CaO, of the order of 27%. 65

19. A friction lining suitable for brakes, clutches, and other applications, substantially as herein described with reference to any one of the accompanying Examples I to V.

Printed for Her Majesty's Stationery Office by Burgess & Son (Abingdon) Ltd.—1982.
Published at The Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from which copies may be obtained.